

	PRESALE DATA					RAPID	STAPLE DATA		COLOUR DATA	
	LOTS	BALES	B/L	BALE WT	WT		LOTS	AR%	LOTS	AR%
2015/2016:										
Queensland	759	4443	5.85	181.5		5.7	540	78.5	0	0.0
NSW	9622	50559	5.25	178.2		11.6	6317	71.1	15	0.5
Victoria	7278	44634	6.13	178.3		49.5	5033	71.7	16	0.3
Tasmania	796	4812	6.05	179.0		29.3	555	70.1	0	0.0
SA	2401	15617	6.50	181.4		21.9	1910	85.8	5	0.6
WA	3529	25277	7.16	179.1		79.7	2729	81.8	0	0.0
Australia	24385	145342	5.96	178.9		34.2	17084	74.9	36	0.3
TYPE:										
Fleece	15089	101661	6.74	180.9		33.0	13118	87.8	0	0.0
Skirting	6342	30352	4.79	174.9		35.0	3707	60.8	36	1.5
Carding	2954	13329	4.51	172.0		38.3	259	9.0	0	0.0
2016/2017:										
Queensland	739	4383	5.93	183.0		3.8	506	75.8	0	0.0
NSW	10334	54519	5.28	179.1		11.8	6621	69.9	4	0.1
Victoria	7734	49368	6.38	179.9		50.2	5163	69.4	1	0.0
Tasmania	977	5974	6.11	179.3		34.5	625	63.3	0	0.0
SA	3013	19287	6.40	183.1		28.1	2342	84.6	7	0.3
WA	4358	30714	7.05	178.0		78.1	3319	80.1	0	0.0
Australia	27155	164245	6.05	179.7		35.8	18576	73.3	12	0.1
TYPE:										
Fleece	16758	115026	6.86	181.5		35.5	14324	86.2	0	0.0
Skirting	6927	33139	4.78	176.4		35.4	3958	59.3	12	0.4
Carding	3470	16080	4.63	173.9		38.1	294	10.0	0	0.0
DIFFERENCES:										
Queensland	2.6-	1.4-	0.08	0.8	0.5-	1.9-	6.3-	2.7-	0.0	0.0
NSW	7.4	7.8	0.03	0.5	8.4	0.2	4.8	1.2-	73.3-	0.4-
Victoria	6.3	10.6	0.25	0.9	11.6	0.7	2.6	2.3-	93.8-	0.3-
Tasmania	22.7	24.1	0.06	0.2	24.4	5.2	12.6	6.8-	0.0	0.0
SA	25.5	23.5	0.10-	0.9	24.7	6.2	22.6	1.2-	40.0	0.3-
WA	23.5	21.5	0.11-	0.6-	20.8	1.6-	21.6	1.7-	0.0	0.0
Australia	11.4	13.0	0.09	0.4	13.6	1.6	8.7	1.6-	66.7-	0.2-
Fleece	11.1	13.1	0.12	0.3	13.5	2.5	9.2	1.6-	0.0	0.0
Skirting	9.2	9.2	0.01-	0.9	10.1	0.4	6.8	1.5-	66.7-	1.1-
Carding	17.5	20.6	0.12	1.1	22.0	0.2-	13.5	1.0	0.0	0.0

NOTE: Differences for LOTS, BALES, AV BALE WT, WT, PROJECTED WT, L&S and COLOUR are % differences.

Differences for LOT-SIZE (B/L), RAPID% and AR% are actual values.

Adoption Rate (AR%) data is based on number of bales tested as a % of number of bales tested for YIELD.

Adoption Rate (AR%) for STAPLE and COLOUR Data is based on all wool tested.

	PRESALE DATA					PROJ WT	RAPID	STAPLE DATA		COLOUR DATA	
	LOTS	BALES	B/L	BALE WT	WT			LOTS	AR%	LOTS	AR%
2015/2016:											
Queensland	1189	7271	6.12	182.2			5.3	849	77.7	0	0.0
NSW	16294	85763	5.26	178.3			11.4	10409	70.0	19	0.3
Victoria	12384	73703	5.95	178.0			47.9	8195	68.6	19	0.2
Tasmania	1618	10258	6.34	177.4			35.8	988	58.3	0	0.0
SA	4048	24981	6.17	181.0			24.2	3123	83.7	6	0.4
WA	5513	39070	7.09	178.4			78.5	4151	79.4	0	0.0
Australia	41046	241046	5.87	178.6			33.5	27715	72.3	44	0.2
TYPE:											
Fleece	24893	165611	6.65	180.7			32.6	21203	86.0	0	0.0
Skirting	10658	50593	4.75	174.6			34.2	5982	57.7	44	1.0
Carding	5495	24842	4.52	172.2			35.9	530	10.6	0	0.0
2016/2017:											
Queensland	1178	6968	5.92	183.8			5.3	797	75.0	0	0.0
NSW	15962	85366	5.35	179.5			11.7	9999	68.6	8	0.1
Victoria	11885	73350	6.17	180.1			47.3	7907	69.5	7	0.1
Tasmania	1811	11055	6.10	178.5			29.3	1151	63.1	0	0.0
SA	4321	27156	6.28	183.2			26.9	3301	83.7	7	0.2
WA	6545	46337	7.08	178.1			76.2	4887	78.2	0	0.0
Australia	41702	250232	6.00	179.9			34.1	28042	72.2	22	0.1
TYPE:											
Fleece	25548	173901	6.81	181.7			33.9	21556	85.3	0	0.0
Skirting	10594	50601	4.78	176.7			33.8	5953	58.2	22	0.4
Carding	5560	25730	4.63	173.9			35.9	533	11.3	0	0.0
DIFFERENCES:											
Queensland	0.9-	4.2-	0.20-	0.9	3.3-	11.6-	0.0	6.1-	2.7-	0.0	0.0
NSW	2.0-	0.5-	0.09	0.7	0.2	2.6-	0.3	3.9-	1.4-	57.9-	0.2-
Victoria	4.0-	0.5-	0.22	1.2	0.7	1.2-	0.6-	3.5-	0.9	63.2-	0.1-
Tasmania	11.9	7.8	0.24-	0.6	8.5	12.9	6.5-	16.5	4.8	0.0	0.0
SA	6.7	8.7	0.11	1.2	10.0	10.9	2.7	5.7	0.0	16.7	0.2-
WA	18.7	18.6	0.01-	0.2-	18.4	14.9	2.3-	17.7	1.2-	0.0	0.0
Australia	1.6	3.8	0.13	0.7	4.6	1.8	0.6	1.2	0.1-	50.0-	0.1-
Fleece	2.6	5.0	0.16	0.6	5.6		1.3	1.7	0.7-	0.0	0.0
Skirting	0.6-	0.0	0.03	1.2	1.2		0.4-	0.5-	0.5	50.0-	0.6-
Carding	1.2	3.6	0.11	1.0	4.6		0.0	0.6	0.7	0.0	0.0

NOTE: Differences for LOTS, BALES, AV BALE WT, WT, PROJECTED WT, L&S and COLOUR are % differences.

Differences for LOT-SIZE (B/L), RAPID% and AR% are actual values.

The change in PROJECTED WT of wool tested = the % change in WT, adjusted for differences in the WT tested at the end of AUGUST as a % of the 12 months total, over the last 3 years.

Adoption Rate (AR%) data is based on number of bales tested as a % of number of bales tested for YIELD.

Adoption Rate (AR%) for STAPLE and COLOUR data is based on all wool tested.

Change in SUPERFINE production (ktonnes) = 3.6%.

It has moved from 47.6% of the clip at the end of AUGUST last year to 47.2% this year.

	TEST RESULTS													
	YIELD	VM	MFD	CVD	SL	CVSL	SS	CVSS	MIDBRK	TIPBRK	HAUT		Y	Y-Z
2015/2016:														
Queensland	64.8	1.7	19.2	21.2	85.0	15.6	34.1	36.5	60.6	24.0	69.1		0.0	0.0
NSW	66.3	2.3	20.2	20.9	89.6	15.3	37.1	34.1	52.5	17.6	73.6		71.6	8.8
Victoria	64.3	1.6	20.7	21.6	90.6	15.2	36.0	37.3	46.4	12.3	75.5		72.0	8.8
Tasmania	71.1	0.9	20.5	21.2	87.6	15.4	41.8	30.5	46.6	25.3	75.2		0.0	0.0
SA	62.2	2.2	20.9	20.9	94.3	15.0	32.4	40.8	45.1	15.1	77.3		71.2	8.9
WA	61.3	1.8	19.8	21.2	91.1	15.7	30.5	39.9	48.7	14.3	72.9		0.0	0.0
Australia	64.5	1.9	20.4	21.2	90.5	15.3	35.0	36.9	49.2	15.6	74.4		71.6	8.8
TYPE:														
Fleece	68.0	1.1	20.5	20.5	92.7	14.4	36.0	36.0	48.5	14.7	76.7		0.0	0.0
Skirting	55.3	4.5	19.6	22.0	81.2	19.9	30.0	42.4	53.8	17.8	63.6		71.6	8.8
Carding	57.6	2.9	20.8	24.8	64.8	17.5	34.4	26.4	30.1	45.0	56.3		0.0	0.0
2016/2017:														
Queensland	63.5	2.7	19.3	21.2	86.2	15.1	34.0	37.3	55.6	30.6	70.3		0.0	0.0
NSW	65.4	2.8	20.2	21.0	89.6	15.2	37.3	34.1	48.8	17.9	73.9		68.6	8.5
Victoria	63.2	2.2	21.0	21.6	91.1	15.4	35.8	36.7	47.8	13.3	75.0		69.1	9.2
Tasmania	70.1	0.6	21.1	21.8	89.2	15.1	35.2	33.8	55.2	27.7	72.0		0.0	0.0
SA	61.7	2.7	20.7	21.1	92.3	15.3	35.2	37.1	50.5	12.0	75.2		68.7	8.8
WA	63.6	1.2	19.8	21.3	88.9	16.1	32.3	36.7	54.7	19.8	71.3		0.0	0.0
Australia	64.1	2.2	20.4	21.3	90.1	15.4	35.4	35.9	50.3	16.8	73.7		68.7	8.8
TYPE:														
Fleece	67.7	1.2	20.6	20.6	92.4	14.5	36.5	35.0	49.9	16.2	76.3		0.0	0.0
Skirting	54.2	5.2	19.5	22.1	80.4	20.2	30.0	41.1	54.1	18.4	62.1		68.7	8.8
Carding	57.7	3.3	21.0	24.6	64.1	19.0	31.7	24.1	32.3	35.7	50.4		0.0	0.0
DIFFERENCES:														
Queensland	1.3-	1.0	0.1	0.0	1.2	0.5-	0.1-	0.8	5.0-	6.6	1.2		0.0	0.0
NSW	0.9-	0.5	0.0	0.1	0.0	0.1-	0.2	0.0	3.7-	0.3	0.3		3.0-	0.3-
Victoria	1.1-	0.6	0.3	0.0	0.5	0.2	0.2-	0.6-	1.4	1.0	0.5-		2.9-	0.4
Tasmania	1.0-	0.3-	0.6	0.6	1.6	0.3-	6.6-	3.3	8.6	2.4	3.2-		0.0	0.0
SA	0.5-	0.5	0.2-	0.2	2.0-	0.3	2.8	3.7-	5.4	3.1-	2.1-		2.5-	0.1-
WA	2.3	0.6-	0.0	0.1	2.2-	0.4	1.8	3.2-	6.0	5.5	1.6-		0.0	0.0
Australia	0.4-	0.3	0.0	0.1	0.4-	0.1	0.4	1.0-	1.1	1.2	0.7-		2.9-	0.0
Fleece	0.3-	0.1	0.1	0.1	0.3-	0.1	0.5	1.0-	1.4	1.5	0.4-		0.0	0.0
Skirting	1.1-	0.7	0.1-	0.1	0.8-	0.3	0.0	1.3-	0.3	0.6	1.5-		2.9-	0.0
Carding	0.1	0.4	0.2	0.2-	0.7-	1.5	2.7-	2.3-	2.2	9.3-	5.9-		0.0	0.0

NOTE: Hauteur is calculated using the TEAM-3 formulae as of July 1st, 2006.

	TEST RESULTS														
	YIELD	VM	MFD	CVD	SL	CVSL	SS	CVSS	MIDBRK	TIPBRK	HAUT	Y	Y-Z		
2015/2016:															
Queensland	64.4	1.7	19.4	21.2	84.6	15.5	33.8	36.4	61.1	22.4	68.8	0.0	0.0		
NSW	65.6	2.3	20.4	21.0	88.4	15.4	37.3	33.8	52.8	16.7	73.0	71.5	8.9		
Victoria	64.0	1.6	20.9	21.8	89.1	15.4	36.6	36.4	46.3	12.1	74.8	71.9	8.7		
Tasmania	70.5	0.8	21.7	21.7	87.6	15.6	40.7	31.4	48.4	25.2	74.6	0.0	0.0		
SA	61.8	2.1	20.9	21.0	92.4	15.1	33.2	39.8	45.1	14.4	76.6	71.3	8.9		
WA	60.9	1.9	19.7	21.4	88.9	15.8	30.5	39.7	47.7	15.2	71.7	0.0	0.0		
Australia	64.1	1.9	20.5	21.4	89.0	15.4	35.4	36.3	49.2	15.3	73.6	71.5	8.8		
TYPE:															
Fleece	67.6	1.1	20.7	20.6	91.2	14.5	36.5	35.5	48.5	14.5	76.1	0.0	0.0		
Skirting	55.2	4.4	19.7	22.3	80.1	20.0	30.1	41.6	53.8	16.9	62.8	71.5	8.8		
Carding	58.0	2.9	21.1	24.8	64.9	17.4	36.0	27.4	35.9	40.2	57.3	0.0	0.0		
2016/2017:															
Queensland	63.0	2.6	19.5	21.5	86.2	15.1	33.3	37.6	55.5	30.9	70.1	0.0	0.0		
NSW	64.8	2.9	20.2	20.9	89.6	15.2	37.5	34.1	49.1	19.0	74.0	68.8	9.8		
Victoria	63.0	2.1	20.9	21.7	89.9	15.4	36.3	36.0	47.4	14.2	74.5	68.9	8.3		
Tasmania	69.6	0.6	21.2	21.7	89.0	15.2	34.9	34.5	52.8	30.0	72.2	0.0	0.0		
SA	61.4	2.7	20.7	21.2	91.3	15.3	35.2	36.9	50.4	12.2	74.5	68.7	8.8		
WA	63.0	1.3	19.7	21.5	87.0	16.4	32.0	36.3	52.2	19.0	70.1	0.0	0.0		
Australia	63.7	2.2	20.4	21.3	89.3	15.5	35.6	35.6	49.7	17.5	73.2	68.8	9.1		
TYPE:															
Fleece	67.3	1.2	20.6	20.6	91.5	14.5	36.7	34.7	49.3	17.0	75.8	0.0	0.0		
Skirting	54.1	5.2	19.5	22.1	79.9	20.3	30.1	40.8	53.5	18.8	61.8	68.8	9.1		
Carding	57.8	3.3	21.0	24.6	64.1	19.0	32.3	25.3	34.1	35.9	51.5	0.0	0.0		
DIFFERENCES:															
Queensland	1.4-	0.9	0.1	0.3	1.6	0.4-	0.5-	1.2	5.6-	8.5	1.3	0.0	0.0		
NSW	0.8-	0.6	0.2-	0.1-	1.2	0.2-	0.2	0.3	3.7-	2.3	1.0	2.7-	0.9		
Victoria	1.0-	0.5	0.0	0.1-	0.8	0.0	0.3-	0.4-	1.1	2.1	0.3-	3.0-	0.4-		
Tasmania	0.9-	0.2-	0.5-	0.0	1.4	0.4-	5.8-	3.1	4.4	4.8	2.4-	0.0	0.0		
SA	0.4-	0.6	0.2-	0.2	1.1-	0.2	2.0	2.9-	5.3	2.2-	2.1-	2.6-	0.1-		
WA	2.1	0.6-	0.0	0.1	1.9-	0.6	1.5	3.4-	4.5	3.8	1.6-	0.0	0.0		
Australia	0.4-	0.3	0.1-	0.1-	0.3	0.1	0.2	0.7-	0.5	2.2	0.4-	2.7-	0.3		
Fleece	0.3-	0.1	0.1-	0.0	0.3	0.0	0.2	0.8-	0.8	2.5	0.3-	0.0	0.0		
Skirting	1.1-	0.8	0.2-	0.2-	0.2-	0.3	0.0	0.8-	0.3-	1.9	1.0-	2.7-	0.3		
Carding	0.2-	0.4	0.1-	0.2-	0.8-	1.6	3.7-	2.1-	1.8-	4.3-	5.8-	0.0	0.0		

NOTE: Hauteur is calculated using the TEAM-3 formulae as of July 1st, 2006.

	PRESALE DATA			STAPLE DATA		COLOUR DATA		TEST RESULTS								
	LOTS	BALES	WEIGHT	LOTS	AR%	LOTS	AR%	YIELD	VM	MFD	CVD	SL	SS	MIDBRK	HAUT	YELL
2015/2016:																
Queensland	1189	7271		849	77.7	0	0.0	64.4	1.7	19.4	21.2	84.6	33.8	61.1	68.8	0.0
NSW	16294	85763		10409	70.0	19	0.3	65.6	2.3	20.4	21.0	88.4	37.3	52.8	73.0	8.9
Victoria	12384	73703		8195	68.6	19	0.2	64.0	1.6	20.9	21.8	89.1	36.6	46.3	74.8	8.7
Tasmania	1618	10258		988	58.3	0	0.0	70.5	0.8	21.7	21.7	87.6	40.7	48.4	74.6	0.0
SA	4048	24981		3123	83.7	6	0.4	61.8	2.1	20.9	21.0	92.4	33.2	45.1	76.6	8.9
WA	5513	39070		4151	79.4	0	0.0	60.9	1.9	19.7	21.4	88.9	30.5	47.7	71.7	0.0
Australia	41046	241046		27715	72.3	44	0.2	64.1	1.9	20.5	21.4	89.0	35.4	49.2	73.6	8.8
TYPE:																
Fleece	24893	165611		21203	86.0	0	0.0	67.6	1.1	20.7	20.6	91.2	36.5	48.5	76.1	0.0
Skirting	10658	50593		5982	57.7	44	1.0	55.2	4.4	19.7	22.3	80.1	30.1	53.8	62.8	8.8
Carding	5495	24842		530	10.6	0	0.0	58.0	2.9	21.1	24.8	64.9	36.0	35.9	57.3	0.0
2016/2017:																
Queensland	1178	6968		797	75.0	0	0.0	63.0	2.6	19.5	21.5	86.2	33.3	55.5	70.1	0.0
NSW	15962	85366		9999	68.6	8	0.1	64.8	2.9	20.2	20.9	89.6	37.5	49.1	74.0	9.8
Victoria	11885	73350		7907	69.5	7	0.1	63.0	2.1	20.9	21.7	89.9	36.3	47.4	74.5	8.3
Tasmania	1811	11055		1151	63.1	0	0.0	69.6	0.6	21.2	21.7	89.0	34.9	52.8	72.2	0.0
SA	4321	27156		3301	83.7	7	0.2	61.4	2.7	20.7	21.2	91.3	35.2	50.4	74.5	8.8
WA	6545	46337		4887	78.2	0	0.0	63.0	1.3	19.7	21.5	87.0	32.0	52.2	70.1	0.0
Australia	41702	250232		28042	72.2	22	0.1	63.7	2.2	20.4	21.3	89.3	35.6	49.7	73.2	9.1
TYPE:																
Fleece	25548	173901		21556	85.3	0	0.0	67.3	1.2	20.6	20.6	91.5	36.7	49.3	75.8	0.0
Skirting	10594	50601		5953	58.2	22	0.4	54.1	5.2	19.5	22.1	79.9	30.1	53.5	61.8	9.1
Carding	5560	25730		533	11.3	0	0.0	57.8	3.3	21.0	24.6	64.1	32.3	34.1	51.5	0.0
DIFFERENCES:																
Queensland	0.9-	4.2-	3.3-	6.1-	2.7-	0.0	0.0	1.4-	0.9	0.1	0.3	1.6	0.5-	5.6-	1.3	0.0
NSW	2.0-	0.5-	0.2	3.9-	1.4-	57.9-	0.2-	0.8-	0.6	0.2-	0.1-	1.2	0.2	3.7-	1.0	0.9
Victoria	4.0-	0.5-	0.7	3.5-	0.9	63.2-	0.1-	1.0-	0.5	0.0	0.1-	0.8	0.3-	1.1	0.3-	0.4-
Tasmania	11.9	7.8	8.5	16.5	4.8	0.0	0.0	0.9-	0.2-	0.5-	0.0	1.4	5.8-	4.4	2.4-	0.0
SA	6.7	8.7	10.0	5.7	0.0	16.7	0.2-	0.4-	0.6	0.2-	0.2	1.1-	2.0	5.3	2.1-	0.1-
WA	18.7	18.6	18.4	17.7	1.2-	0.0	0.0	2.1	0.6-	0.0	0.1	1.9-	1.5	4.5	1.6-	0.0
Australia	1.6	3.8	4.6	1.2	0.1-	50.0-	0.1-	0.4-	0.3	0.1-	0.1-	0.3	0.2	0.5	0.4-	0.3
Fleece	2.6	5.0	5.6	1.7	0.7-	0.0	0.0	0.3-	0.1	0.1-	0.0	0.3	0.2	0.8	0.3-	0.0
Skirting	0.6-	0.0	1.2	0.5-	0.5	50.0-	0.6-	1.1-	0.8	0.2-	0.2-	0.2-	0.0	0.3-	1.0-	0.3
Carding	1.2	3.6	4.6	0.6	0.7	0.0	0.0	0.2-	0.4	0.1-	0.2-	0.8-	3.7-	1.8-	5.8-	0.0

NOTE: AR% = Adoption Rate %, i.e. % of number of bales tested for Staple Measurement and Colour (Average Yellowness).

Differences in LOTS, BALES, and WEIGHT are year-on-year % differences.

Differences in ADOPTION RATE % and in the TEST RESULTS are year-on-year actual differences.

Change in SUPERFINE production (ktonnes) = 3.6%.

It has moved from 47.6% of the clip at the end of AUGUST last year to 47.2% this year.

Hauteur is calculated using the TEAM-3 formulae as of July 1st, 2006.

	WEIGHT (tonnes)					ALL WOOL	PERCENTAGE OF TOTAL CLIP				
	0.0-16.5	16.6-17.5	17.6-18.5	18.6-19.5	0.0-19.5		0.0-16.5	16.6-17.5	17.6-18.5	18.6-19.5	0.0-19.5
2015/2016:											
Queensland	56.3	136.9	234.1	382.4	809.7		4.3	10.3	17.7	28.9	61.1
NSW	869.1	1962.1	2639.4	3185.3	8655.9		5.7	12.8	17.3	20.8	56.6
Victoria	642.5	1101.6	1732.7	2088.6	5565.3		4.9	8.4	13.2	15.9	42.4
Tasmania	134.6	281.6	429.5	230.8	1076.5		7.4	15.5	23.6	12.7	59.2
SA	24.2	92.6	279.9	575.7	972.4		0.5	2.0	6.2	12.7	21.5
WA	148.1	461.5	1075.3	1713.0	3397.9		2.1	6.6	15.4	24.6	48.8
Australia	1874.8	4036.3	6390.9	8175.7	20477.8		4.4	9.4	14.8	19.0	47.6
TYPE:											
Fleece	1207.9	2631.3	3840.1	5267.9	12947.2		4.0	8.8	12.8	17.6	43.3
Skirting	496.5	1043.1	1852.9	2196.2	5588.7		5.6	11.8	21.0	24.9	63.3
Carding	170.4	361.9	698.0	711.6	1941.9		4.0	8.5	16.3	16.6	45.4
2016/2017:											
Queensland	48.0	96.8	213.7	409.6	768.1		3.7	7.6	16.7	32.0	60.0
NSW	1100.5	1959.9	2576.4	2826.4	8463.1		7.2	12.8	16.8	18.4	55.2
Victoria	640.7	1145.6	1576.3	2052.9	5415.6		4.9	8.7	11.9	15.5	41.0
Tasmania	161.6	401.1	449.0	223.4	1235.1		8.2	20.3	22.7	11.3	62.6
SA	49.4	124.7	324.6	769.4	1268.0		1.0	2.5	6.5	15.5	25.5
WA	113.2	498.3	1396.6	2066.9	4075.0		1.4	6.0	16.9	25.0	49.4
Australia	2113.3	4226.4	6536.6	8348.6	21224.9		4.7	9.4	14.5	18.5	47.2
TYPE:											
Fleece	1366.3	2678.1	4071.8	5275.9	13392.0		4.3	8.5	12.9	16.7	42.4
Skirting	569.2	1153.3	1746.5	2333.9	5802.8		6.4	12.9	19.5	26.1	64.9
Carding	177.9	395.0	718.4	738.8	2030.1		4.0	8.8	16.1	16.5	45.4
DIFFERENCES:											
Queensland	14.7-	29.3-	8.7-	7.1	5.1-	3.4-	0.6-	2.7-	1.0-	3.1	1.1-
NSW	26.6	0.1-	2.4-	11.3-	2.2-	0.2	1.5	0.0	0.5-	2.4-	1.4-
Victoria	0.3-	4.0	9.0-	1.7-	2.7-	0.7	0.0	0.3	1.3-	0.4-	1.4-
Tasmania	20.1	42.4	4.5	3.2-	14.7	8.5	0.8	4.8	0.9-	1.4-	3.4
SA	104.1	34.7	16.0	33.6	30.4	10.0	0.5	0.5	0.3	2.8	4.0
WA	23.6-	8.0	29.9	20.7	19.9	18.4	0.7-	0.6-	1.5	0.4	0.6
Australia	12.7	4.7	2.3	2.1	3.6	4.6	0.3	0.0	0.3-	0.5-	0.4-
Fleece	13.1	1.8	6.0	0.2	3.4	5.6	0.3	0.3-	0.1	0.9-	0.9-
Skirting	14.6	10.6	5.7-	6.3	3.8	1.2	0.8	1.1	1.5-	1.2	1.6
Carding	4.4	9.1	2.9	3.8	4.5	4.6	0.0	0.3	0.2-	0.1-	0.0

	WEIGHT (tonnes)					ALL WOOL	PERCENTAGE OF TOTAL CLIP				
	0.0-12.5	12.6-13.5	13.6-14.5	14.6-15.5	15.6-16.5		0.0-12.5	12.6-13.5	13.6-14.5	14.6-15.5	15.6-16.5
2015/2016:											
Queensland	0.0	0.0	0.0	6.0	50.4		0.0	0.0	0.0	0.4	3.8
NSW	0.0	0.0	5.2	161.4	702.5		0.0	0.0	0.0	1.1	4.6
Victoria	0.0	1.1	15.6	132.4	493.3		0.0	0.0	0.1	1.0	3.8
Tasmania	0.0	0.0	0.0	23.1	111.5		0.0	0.0	0.0	1.3	6.1
SA	0.0	0.0	0.0	4.3	19.9		0.0	0.0	0.0	0.1	0.4
WA	0.0	0.0	0.0	15.8	132.3		0.0	0.0	0.0	0.2	1.9
Australia	0.0	1.1	20.8	343.1	1509.9		0.0	0.0	0.0	0.8	3.5
TYPE:											
Fleece	0.0	0.2	12.5	228.1	967.1		0.0	0.0	0.0	0.8	3.2
Skirting	0.0	0.9	4.5	88.1	403.1		0.0	0.0	0.1	1.0	4.6
Carding	0.0	0.0	3.8	26.9	139.7		0.0	0.0	0.1	0.6	3.3
2016/2017:											
Queensland	0.0	0.0	0.0	6.0	42.0		0.0	0.0	0.0	0.5	3.3
NSW	0.0	0.3	12.7	177.0	910.4		0.0	0.0	0.1	1.2	5.9
Victoria	0.0	0.0	19.1	120.1	501.6		0.0	0.0	0.1	0.9	3.8
Tasmania	0.0	0.0	0.3	17.9	143.5		0.0	0.0	0.0	0.9	7.3
SA	0.0	0.0	0.0	4.3	45.0		0.0	0.0	0.0	0.1	0.9
WA	0.0	0.0	0.0	8.7	104.6		0.0	0.0	0.0	0.1	1.3
Australia	0.0	0.3	32.0	333.9	1747.1		0.0	0.0	0.1	0.7	3.9
TYPE:											
Fleece	0.0	0.3	22.0	218.2	1125.8		0.0	0.0	0.1	0.7	3.6
Skirting	0.0	0.0	6.4	80.4	482.4		0.0	0.0	0.1	0.9	5.4
Carding	0.0	0.0	3.7	35.4	138.9		0.0	0.0	0.1	0.8	3.1
DIFFERENCES:											
Queensland	0.0	0.0	0.0	0.0	16.7-	3.4-	0.0	0.0	0.0	0.1	0.5-
NSW	0.0	0.0	144.2	9.7	29.6	0.2	0.0	0.0	0.1	0.1	1.3
Victoria	0.0	100.0-	22.4	9.3-	1.7	0.7	0.0	0.0	0.0	0.1-	0.0
Tasmania	0.0	0.0	0.0	22.5-	28.7	8.5	0.0	0.0	0.0	0.4-	1.2
SA	0.0	0.0	0.0	0.0	126.1	10.0	0.0	0.0	0.0	0.0	0.5
WA	0.0	0.0	0.0	44.9-	20.9-	18.4	0.0	0.0	0.0	0.1-	0.6-
Australia	0.0	72.7-	53.8	2.7-	15.7	4.6	0.0	0.0	0.1	0.1-	0.4
Fleece	0.0	50.0	76.0	4.3-	16.4	5.6	0.0	0.0	0.1	0.1-	0.4
Skirting	0.0	100.0-	42.2	8.7-	19.7	1.2	0.0	0.0	0.0	0.1-	0.8
Carding	0.0	0.0	2.6-	31.6	0.6-	4.6	0.0	0.0	0.0	0.2	0.2-